



**Liner:** 76lb polycoated bleached kraft, silicone coated on both sides

Liner Side Adhesive: Acrylic (1603)

**Backing/Carrier:** 0.5 mil polyester film

Air Side Adhesive: Acrylic (1603)

## **Applications**

Gasket assembly

 Mounting nameplates, decals, and decorative plastic trim  Laminating paper, felt, sponge rubber, foam, and plastic

## Features Benefits

Polyester Film Carrier	Support for aid in processing and application
	<ul> <li>Easily conforms to various surface types</li> </ul>
<ul> <li>Acrylic Adhesive</li> </ul>	<ul> <li>High initial tack</li> </ul>
	<ul> <li>Resists plasticizer migration</li> </ul>
	<ul> <li>Good adhesion to a wide variety of substrates</li> </ul>
• 76lb Liner	<ul> <li>Dimensionally stable</li> </ul>
	<ul> <li>Good moisture resistance</li> </ul>

## **Typical Test Values**

	Standard UOM	Metric UOM	Test Method
Total Thickness w/liner	8.7 mils	0.221 mm	PSTC 133
Adhesive Thickness (Air Side)	1.3 mils	0.033 mm	PSTC 133
Carrier Thickness	0.5 mils	0.013 mm	PSTC 133
Adhesive Thickness (Liner Side)	1.3 mils	0.033 mm	PSTC 133
Liner Thickness	5.6 mils	0.142 mm	PSTC 133
Adhesion to Steel (Air Side)	40 oz/in	4.38 N/cm	PSTC 101 Mod
Adhesion to Steel (Liner Side)	50 oz/in	5.47 N/cm	PSTC 101 Mod
Shear Strength (Air Side)	<24 hours		PSTC 107
Shear Strength (Liner Side)	<24 hours		PSTC 107
Laminating Temperature	65 to 150 °F	18 to 65 °C	
Maximum Continuous Use	200 °F	93 °C	
Intermittent Use	250 °F	121 °C	

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.

