


## 8433M

## AdMount™ Digital Mounting Tape



**Liner:** 74# Polycoated Kraft

Liner Side Adhesive: Rubber (1912)

**Backing/Carrier:** 0.5 mil Clear PET

Air Side Adhesive: Rubber (1912)

## **Applications**

- Digital imaging and graphic arts uses
- Permanent mounting to most common paper and board stocks

 Mounting uses to FOAM-X®,, Fome-Cor® GATORFOAM®, GATORBOARD®, and Sintra®

Features Benefits

<ul> <li>Rubber Adhesive</li> </ul>	<ul> <li>High tack and high peel adhesion</li> </ul>
	Permanent bonding
	<ul> <li>Bonds to a variety of substrates</li> </ul>
PET Film Carrier	<ul> <li>Provides strength and stability</li> </ul>
	<ul> <li>Conformable</li> </ul>
• 74# Polycoated Kraft Liner	<ul> <li>Good lay-flat; moisture resistant</li> </ul>

## **Typical Test Values**

	Standard UOM	Metric UOM	Test Method
Overall Thickness (w/liner)	8.4 mils	0.213 mm	PSTC 133
Air-Side Adhesive Thickness	1.2 mils	0.030 mm	PSTC 133
Carrier Thickness	0.5 mils	0.013 mm	PSTC 133
Liner Side Adhesive Thickness	1.2 mils	0.030 mm	PSTC 133
Liner Thickness	5.5 mils	0.140 mm	PSTC 133
Adhesion to Steel (Air Side)	80 oz/in	8.75 N/cm	PSTC 101 Mod - 1 mil PET
Adhesion to Steel (Liner Side)	80 oz/in	8.75 N/cm	PSTC 101 Mod - 1 mil PET
Shear Strength	>7 Days		PSTC 107 Mod
Laminating Temperature	68 to 100 °F	20 to 38 °C	
Service Temperature	30 to 150 °F	-1 to 66 °C	

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

Standard Shelf Life: 12 months from date of shipment

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any lead responsibility.

