


4132M-80

Double-Coated Tape Polyester Film Tape



Liner:	80# SCK
Liner Side Adhesive:	Rubber (I923)
Backing/Carrier:	0.5 mil PET Film
Air Side Adhesive:	Rubber (I923)

Applications

- Bonding to a wide variety of foams, felt, cork, rubber, and sponge materials
- Splicing applications
- Weatherstripping
- General purpose bonding uses
- Gasket, insulation, light shielding, and sound damping uses

Features

- Rubber Adhesive System
- Polyester Film Carrier
- 80# SCK Liner

Benefits

- Offers exceptionally high tack and high peel
- Excellent shear strength
- Well-suited for general purpose bonding to medium and high energy substrates
- Air side designed for bonding to various foams, as well as rough and porous surfaces
- Exhibits good bond to LSE substrates
- Support for aid in processing and application
- Conformable and good dimensional stability
- Excellent processing and die-cutting stability

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Overall Thickness (w/liner)	8.4 mils	0.213 mm	PSTC 133
Air-Side Adhesive Thickness	2.0 mils	0.051 mm	PSTC 133
Carrier Thickness	0.5 mils	0.013 mm	PSTC 133
Liner Side Adhesive Thickness	1.2 mils	0.030 mm	PSTC 133
Liner Thickness	4.7 mils	0.119 mm	PSTC 133
Adhesion to Steel (Air Side)	158 oz/in	17.29 N/cm	PSTC 101 Mod - 1 mil PET
Adhesion to Steel (Liner Side)	152 oz/in	16.63 N/cm	PSTC 101 Mod - 1 mil PET
Loop Tack	272 oz/in	29.76 N/cm	PSTC 16 Method A
Shear Strength (1" x 1" x 1Kg)	> 7 Days		PSTC 107 Mod
Laminating Temperature	68 to 100 °F	20 to 38 °C	
Service Temperature	30 to 150 °F	-1 to 66 °C	

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F
 Standard Shelf Life: 12 months from date of shipment

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.