


# **Double-Coated Foam Tape**



**Liner:** 76lb polycoated bleached kraft,

silicone treated on both sides

**LS Adhesive:** Non-sensitizing acrylic (M109)

**Backing/Carrier:** 1/32" white, crosslinked polyethylene

foam

**AS Adhesive:** Non-sensitizing acrylic (M109)

## **Applications**

Electrodes: ECG, EKG, TENS

Medical device assembly

Medical device attachment

#### Features Benefits

<ul> <li>Polyethylene Foam Carrier</li> </ul>	<ul> <li>Soft and flexible for maximum patient comfort</li> </ul>		
	<ul> <li>Conformable and easily adapts to medical</li> </ul>		
	devices and body contours		
Non-Sensitizing Acrylic Adhesive	<ul> <li>High tack and good shear</li> </ul>		
	<ul> <li>Stable to EtO and gamma sterilization</li> </ul>		
• 76lb Release Liner	Easy to die-cut and process		
	<ul> <li>Good dimensional stability and lay flat</li> </ul>		

# **Typical Test Values**

	Standard	UOM Metric UOM		UOM	Test Method
Total Thickness w/liner	39.8	mils	1.011	mm	PSTC 133
Adhesive Thickness (Air Side)	1.4	mils	0.036	mm	PSTC 133
Adhesive Thickness (Liner Side)	1.4	mils	0.036	mm	PSTC 133
Carrier Thickness	31.2	mils	0.792	mm	PSTC 133
Liner Thickness	5.8	mils	0.147	mm	PSTC 133
Adhesion to Steel (Air Side)	150	oz/in	16.41	N/cm	PSTC 101 Mod
Adhesion to Steel (Liner Side)	150	oz/in	16.41	N/cm	PSTC 101 Mod
,	Pı	roduc	t Safety	,	

## Troduct Galety

The base adhesives in this medical product have been tested in accordance with ISO 10993 and found to be non-cytotoxic, non-sensitizing, and non-irritating.

In accordance with FDA cGMP requirements, Berry reminds the customer that ultimate fitness for use must be determined by the manufacturer of the finished device.

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.

