


3614C

Non-Woven Single-Coated Tape



Backing: 1.3 oz/sy white spunlace polyester non-

woven

Adhesive: Non-sensitizing medical-grade acrylic

(M102)

Liner: 72lb white polycoated kraft, silicone

treated on one side

Applications

Electrodes: ECG, EKG, TENS

Wound coverings

Medical device attachment

Island dressings

Features Benefits

PET non-woven carrier	Breathable for maximum patient comfort	
	 Highly conformable 	
 Medical-grade Acrylic Adhesive 	 Designed for long-term wear applications 	
	 Highly resistant to perspiration-borne moisture 	
• 72lb Release Liner	Easy to die-cut and convert	
	 Good dimensional stability and lay flat 	

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Total Thickness w/o Liner	8.6 mils	0.218 mm	PSTC 133
Adhesive Thickness	2.0 mils	0.051 mm	PSTC 133
Liner Thickness	5.6 mils	0.142 mm	PSTC 133
Adhesion to Steel	48 oz/in	5.25 N/cm	PSTC 101 Mod

The base adhesives in this medical product have been tested in accordance with ISO 10993 and found to be non-cytotoxic, non-irritating, and non-sensitizing.

In accordance with FDA cGMP requirements, Berry reminds the customer that ultimate fitness for use must be determined by the manufacturer of the finished device.

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.

