

TECHNICAL BULLETIN

TRANSFER TAPE

PRODUCT:	7832 Acrylic Adhesive Transfer Tape		
PRIMARY USE:	Forms excellent bonds to a variety of ether, ester and low perm urethane foams. Engineered for foam-to-foam bonding.		
DESCRIPTION:	7832 is constructed by coating 2 mils of a high heat-resistant acrylic adhesive on a 74lb liner. 7832 contains a biostatic additive which inhibits microbial growth. Exhibits resistance to many types of migrating plasticizers.		
LINER:	74lb White Poly-coated Kraft		
TYPICAL PHYSICAL PROPERTIES:	Thickness	Adhesive Exposed Side (nominal)	2.0 mils
		74# Poly-coated Kraft Release Liner (nominal)	5.5 mils
	Peel Adhesion	PSTC #101; backed with 1 mil polyester <i>24 Hour Dwell:</i>	
		Exposed Side	55 oz/inch
		Liner Side	NA
		PSTC #101; backed with 2 mil dead soft aluminum foil <i>24 Hour Dwell:</i>	
		Exposed Side	160 oz/inch
		Liner Side	NA
	NOTE: Peel tests are performed as per PSTC #101, which states one minute maximum dwell time. In general, for acrylic adhesives, longer residence time yields much higher peel values.		
	Shear Adhesion	PSTC #107; Modified, @ 72° F.	
		(1" x 1" x 1,000 grams)	7 Days
	Loop Tack	PSTC #16	
		Adhesive Side	60 oz/inch
Line Side		NA	

ADCHEM CORPORATION
1852 Old Country Road
Riverhead, NY 11901
P: 631-727-6000
www.adchem.com

Data presented are typical properties taken from a limited number of production runs and should not be used for specification purposes. Adchem Corporation makes no warranty, expressed or implied, and specifically disclaims and disavows any implied warranty of merchantability and of fitness for a particular purpose. Accordingly, all Adchem products are sold with the understanding that purchasers will be solely responsible for determining the suitability of the materials for any purpose.

TECHNICAL BULLETIN

7832-74 Adhesive Transfer Tape

<p>PRODUCT FEATURES:</p>	<ul style="list-style-type: none"> • Excellent adhesion to a broad spectrum of foam substrates. • Biostatic additive is included to inhibit microbial growth. • Easy release 74lb liner. • Good shear resistance. • Resistance to many plasticizers.
<p>SERVICE TEMPERATURE:</p>	<p>-30°F to 220°F</p> <p>NOTE: This information is provided as a means to help characterize the adhesive's temperature resistance. Note that this data is based on limited testing and under no load. The practical service temperature of this or any adhesive system is dependent on many variables including the substrates being bonded, environmental conditions, and the loading and method of application. The purchaser is responsible for determining the suitability of this or any product for their particular purpose and process. The recommended application temperature is 68°F to 100°F.</p>
<p>NOTES:</p>	<p>The use of heat and pressure will help to increase the initial bond of the product to the substrate. Testing is recommended prior to laminating to any material that contains migrating plasticizers.</p>
<p>RELATED ADCHEM PRODUCTS:</p>	<p>Other high performance acrylic transfer tapes include:</p> <p>7434 – High temperature, aggressive, foam bonding.</p> <p>7834 – Same as 7832 with 4-mils adhesive.</p> <p>7833 – Same as 7832 with 3-mils adhesive.</p> <p>7334 – Moderate tack and peel, general purpose.</p>
<p>SHELF LIFE:</p>	<p>One year from date of shipment when stored under cool, dry conditions.</p>

Rev. 04.04.14

ADCHEM CORPORATION
1852 Old Country Road
Riverhead, NY 11901
P: 631-727-6000
www.adchem.com

Data presented are typical properties taken from a limited number of production runs and should not be used for specification purposes. Adchem Corporation makes no warranty, expressed or implied, and specifically disclaims and disavows any implied warranty of merchantability and of fitness for a particular purpose. Accordingly, all Adchem products are sold with the understanding that purchasers will be solely responsible for determining the suitability of the materials for any purpose.