



Applications

- Gasket assembly
- Mounting nameplates, decals, and plastic trim
- Laminating paper, felt, sponge rubber, foam, and plastics

Features	Benefits	
Polyester Film Carrier	Support for aid in processing and application	
	Conformable	
Acrylic Adhesive	 Excellent anchorage to foams and plastics 	
	• Excellent performance over a wide temperature	
• 74lb Bleached Polycoated Kraft Liner	Easy to die-cut and process	

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Total Thickness w/liner	10.8 mils	0.274 mm	PSTC 133
Adhesive Thickness (Air Side)	2.0 mils	0.051 mm	PSTC 133
Adhesive Thickness (Liner Side)	2.0 mils	0.051 mm	PSTC 133
Carrier Thickness	1.0 mils	0.025 mm	PSTC 133
Liner Thickness	5.8 mils	0.147 mm	PSTC 133
Adhesion to Steel (Air Side)	125 oz/in	13.68 N/cm	PSTC 101 Mod
Adhesion to Steel (Liner Side)	125 oz/in	13.68 N/cm	PSTC 101 Mod
Shear Strength (Air Side)	<24 hours		PSTC 107
Shear Strength (Liner Side)	<24 hours		PSTC 107
Laminating Temperature	50 to 150 °F	10 to 65 °C	
Maximum Continuous Use	200 °F	93 °C	
Intermittent Use	250 °F	121 °C	

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.



25 Forge Pkwy Franklin, MA 02038 1-800-343-7875 Fax 1-800-328-4822 www.berryglobal.com