


## Double-Coated PET Film Tape



- Liner:** 60# Silicone-Coated Densified Kraft
- Liner Side Adhesive:** Rubber (I915)
- Backing/Carrier:** 0.5 mil PET Film
- Air Side Adhesive:** Rubber (I915)

### Applications

- Bonding and laminating to a variety of plastics, metals, and papers
- Laminating to cork, felt, abrasives, and more
- Splicing and general purpose holding

### Features

- Rubber Adhesive
- Polyester Film Carrier
- 60# Kraft Liner

### Benefits

- Excellent quick stick to difficult surfaces
- Moderate shear strength
- Support for aid in processing and application
- Conformable
- Easily die-cut

### Typical Test Values

	Standard UOM	Metric UOM	Test Method
<b>Overall Thickness (w/liner)</b>	6.5 mils	0.165 mm	PSTC 133
<b>Adhesive Thickness (Air Side)</b>	1.25 mils	0.032 mm	PSTC 133
<b>Carrier Thickness</b>	0.5 mils	0.013 mm	PSTC 133
<b>Adhesive Thickness (Liner Side)</b>	1.25 mils	0.032 mm	PSTC 133
<b>Liner Thickness</b>	3.5 mils	0.089 mm	PSTC 133
<b>Adhesion to Steel (Air Side)</b>	110 oz/in	12.03 N/cm	PSTC 101 Mod - 1 mil PET
<b>Adhesion to Steel (Liner Side)</b>	110 oz/in	12.03 N/cm	PSTC 101 Mod - 1 mil PET
<b>Adhesion to Steel (Air Side)</b>	128 oz/in	14.00 N/cm	PSTC 101 Mod - 2 mil Alu Foil
<b>Adhesion to Steel (Liner Side)</b>	128 oz/in	14.00 N/cm	PSTC 101 Mod - 2 mil Alu Foil
<b>Shear Strength</b>	>7 Days		PSTC 107 Mod
<b>Laminating Temperature</b>	68 to 100 °F	20 to 38 °C	
<b>Service Temperature</b>	30 to 150 °F	-1 to 66 °C	

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

Standard Shelf Life: 12 months from date of shipment

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.