




Differential Double-Coated Polyester Film Tape



Liner:12pt Polycoated KraftLiner Side Adhesive:Rubber (I920)Backing/Carrier:0.5 mil PET FilmAir Side Adhesive:Acrylic (I639)Specifications:Chrysler PF-10770(NC); Toyota TSK6712G
GM 3607M Type1, 3622M Type IV
Ford ESA-M11P19-A, ESB-M3G76-B2, ESH-
M11P19-B
Delphi SD2-324 4.1.1, 4.1.4,4.3.3

Applications

Bonding to a variety of ether, ester, and low perm
 LSE bonding including talc-filled polypropylene urethane foams

Features	Benefits	
Acrylic Adhesive	 Excellent heat resistance Low fogging (tested at 24 hrs, 200 °F) Biostatic additive resists microbial growth 	
Polyester Film Carrier	Support for aid in processing and applicationConformable	
Rubber Adhesive	High tackHeat-resistant	
12pt Board Liner	 Rigid liner facilitates processing and application 	

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Overall Thickness (w/liner)	14.8 mils	0.376 mm	PSTC 133
Air-Side Adhesive Thickness	1.5 mils	0.038 mm	PSTC 133
Carrier Thickness	0.5 mils	0.013 mm	PSTC 133
Liner Side Adhesive Thickness	1.5 mils	0.038 mm	PSTC 133
Liner Thickness	11.3 mils	0.287 mm	PSTC 133
Adhesion to Steel (Air Side)	60 oz/in	6.56 N/cm	PSTC 101 Mod - 1 mil PET
Adhesion to Steel (Liner Side)	115 oz/in	12.58 N/cm	PSTC 101 Mod - 1 mil PET
Adhesion to Steel (Air Side)	140 oz/in	15.32 N/cm	PSTC 101 Mod - 2 mil Alu Foil
Adhesion to Steel (Liner Side)	160 oz/in	17.50 N/cm	PSTC 101 Mod - 2 mil Alu Foil
Shear Strength (Room Temp)	>7 Days		PSTC 107 Mod
Laminating Temperature	68 to 100 °F	20 to 38 °C	
Service Temperature	30 to 160 °F	-1 to 71 °C	

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

Standard Shelf Life: 12 months from date of shipment

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.

