

601H Transfer Adhesive

	Release Liner						
	Adhesive Adhesive		Acrylic (1600)				
		Liner:	80lb super-calendered, silicone release treated on both sides				
Applications							
 Mounting name plates, d trim pieces 	ecals, and dec	corative •	Laminating paper, felt, sponge rubber, and plastic				
Features			Benefits				
Acrylic Adhesive		•	High tack adhesive Excellent anchorage to a variety of substrates UV resistant Excellent aging characteristics				
80lb SC Kraft Release Liner		•	Easy liner removal				

Typical Test Values

	71		
	Standard UOM	Metric UOM	Test Method
Total Thickness w/liner	6.8 mils	0.173 mm	PSTC 133
Adhesive Thickness	2.0 mils	0.051 mm	PSTC 133
Liner Thickness	4.8 mils	0.122 mm	PSTC 133
Adhesion to Steel	50 oz/in	5.47 N/cm	PSTC 101 Mod
Shear Strength	168+ hours		PSTC 107
Application Temperature	32 to 180 °F	0 to 82 °C	
Laminating Temperature	60 to 250 °F	16 to 121 °C	
Maximum Continuous Use	200 °F	93 °C	
Intermittent Use	250 °F	121 °C	

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.



25 Forge Pkwy Franklin, MA 02038 1-800-343-7875 Fax 1-800-328-4822 www.berryglobal.com