





_	••							
٠	Laminating and bonding to ether and ester foams	•	Applications requiring resistance to microbial					
	and low-perm urethane foams		growth					

Benefits		
High peel adhesion		
High shear strength		
Biostatic additive resists microbial growth		
Excellent adhesion to a broad spectrum of foams		
Conformable and good dimensional stability		

Typical Test Values							
	Standard UOM	Metric UOM	Test Method				
Adhesive Thickness	4.0 mils	0.102 mm	PSTC 133				
Liner Thickness	5.5 mils	0.140 mm	PSTC 133				
Adhesion to Steel	65 oz/in	7.11 N/cm	PSTC 101 Mod - 1 mil PET				
Adhesion to Steel	165 oz/in	18.05 N/cm	PSTC 101 Mod - 2 mil Alu Foil				
Shear Strength (at 72 °F)	7 Days		PSTC 107 Mod				
Laminating Temperature	erature 68 to 100 °F 20 to 38 °C						
Service Temperature	-30 to 220 °F	-34 to 104 °C					

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

Standard Shelf Life: 12 months from date of shipment

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.

