


## Double-Coated AdMount™ Banner Tape



**Liner:** 74# Polycoated Kraft

**Liner Side Adhesive:** Acrylic (I643)

**Backing/Carrier:** 0.5 mil PET Film

**Air Side Adhesive:** Acrylic (I643)

### Applications

- Laminating and bonding vinyl products used in flooring, wall coverings, synthetic leather, and sheet or roll goods
- Seaming and hemming banners
- Applications where a heavy adhesive mass is preferred

### Features

- Acrylic Adhesive
- Polyester Film Carrier
- 74# Polycoated Kraft Liner

### Benefits

- Heavy mass for exceptional surface wet-out
- Good plasticizer resistance
- UV Resistant
- Excellent tack
- Bonds to a variety of substrates
- Support for aid in processing and application
- Conformable
- Good lay-flat; moisture resistant

### Typical Test Values

	Standard UOM	Metric UOM	Test Method
<b>Overall Thickness (w/liner)</b>	13.0 mils	0.330 mm	PSTC 133
<b>Air-Side Adhesive Thickness</b>	3.5 mils	0.089 mm	PSTC 133
<b>Carrier Thickness</b>	0.5 mils	0.013 mm	PSTC 133
<b>Liner Side Adhesive Thickness</b>	3.5 mils	0.089 mm	PSTC 133
<b>Liner Thickness</b>	5.5 mils	0.140 mm	PSTC 133
<b>Adhesion to Steel (Air Side)</b>	54 oz/in	5.91 N/cm	PSTC 101 Mod - 1 mil PET
<b>Adhesion to Steel (Liner Side)</b>	48 oz/in	5.25 N/cm	PSTC 101 Mod - 1 mil PET
<b>Adhesion to Steel (Air Side)</b>	120 oz/in	13.13 N/cm	PSTC 101 Mod - 2 mil Alu Foil
<b>Adhesion to Steel (Liner Side)</b>	125 oz/in	13.68 N/cm	PSTC 101 Mod - 2 mil Alu Foil
<b>Loop Tack (Air Side)</b>	80 oz/in	8.75 N/cm	PSTC 16
<b>Loop Tack (Liner Side)</b>	50 oz/in	5.47 N/cm	PSTC 16
<b>Shear Strength</b>	6 Days		PSTC 107 Mod
<b>Laminating Temperature</b>	68 to 100 °F	20 to 38 °C	
<b>Service Temperature</b>	-30 to 220 °F	-34 to 104 °C	

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F  
Standard Shelf Life: 12 months from date of shipment

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.