


## 9002



 Laminating and bonding to low-surface energy materials and silicone foams

## Applications

• Ideal for use in high temperature and harsh environments

Features	Benefits
Silicone Adhesive	High peel strength adhesive
	<ul> <li>Exceptional high temperature performance</li> </ul>
	<ul> <li>Good bond to LSE substrates</li> </ul>
PET Film Liner	Conformable and good dimensional stability

Typical	Test	Va	lues
1 y pio ai	1001		1005

	Standard UOM	Metric UOM	Test Method		
Adhesive Thickness	2.0 mils	0.051 mm	PSTC 133		
Liner Thickness	2.0 mils	0.051 mm	PSTC 133		
Adhesion to Steel	43 oz/in	4.70 N/cm	PSTC 101 Mod - 1 mil PET		
Adhesion to Polypropylene	38 oz/in	4.16 N/cm	PSTC 101 Mod - 2 mil Alu Foil		
Shear Strength (at 72 °F)	>7 Days		PSTC 107 Mod		
Loop Tack	22 oz/in	2.41 N/cm	PSTC 16		
Laminating Temperature	68 to 100 °F	20 to 38 °C			
Service Temperature	-100 to 500 °F	-73 to 260 °C			

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

Standard Shelf Life: 12 months from date of shipment

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.

