


**Admount® Graphic Arts Mounting Tape**



**Liner:** 74# Polycoated Kraft

**Liner Side Adhesive:** Acrylic (I632)

**Backing/Carrier:** 1.4 mil White PP

**Air Side Adhesive:** Acrylic (I632)

**Applications**

- Graphic arts uses for wide format digital and photographic print mounting

**Features**

**Benefits**

- |   |   |
|---|---|
| <ul style="list-style-type: none"> <li>• Acrylic Adhesive</li> <li>• PE Film Carrier</li> <li>• 74# Polycoated Kraft Liner</li> </ul> | <ul style="list-style-type: none"> <li>• Acid-free and pH neutral</li> <li>• Smooth coating for even application</li> <li>• UV Resistant</li> <li>• Thick and opaque to brighten prints</li> <li>• Conformable</li> <li>• Good stay-flat and moisture resistance</li> </ul> |
|---|---|

**Typical Test Values**

	Standard UOM	Metric UOM	Test Method
<b>Overall Thickness (w/liner)</b>	9.1 mils	0.231 mm	PSTC 133
<b>Air-Side Adhesive Thickness</b>	1.1 mils	0.028 mm	PSTC 133
<b>Carrier Thickness</b>	1.4 mils	0.036 mm	PSTC 133
<b>Liner Side Adhesive Thickness</b>	1.1 mils	0.028 mm	PSTC 133
<b>Liner Thickness</b>	5.5 mils	0.140 mm	PSTC 133
<b>Adhesion to Steel (Air Side)</b>	60 oz/in	6.56 N/cm	PSTC 101 Mod
<b>Adhesion to Steel (Liner Side)</b>	60 oz/in	6.56 N/cm	PSTC 101 Mod
<b>Shear Strength</b>	>7 Days		PSTC 107 Mod
<b>Laminating Temperature</b>	68 to 100 °F	20 to 38 °C	
<b>Service Temperature</b>	-30 to 220 °F	-34 to 104 °C	

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

Standard Shelf Life: 12 months from date of shipment

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.