
POLYKEN® 2932P

Single-Coated Foam Tape



Backing: 1/32" white, crosslinked polyethylene

foam

Adhesive: Non-sensitizing medical grade acrylic

(M108)

Liner: 96lb bleached polycoated kraft, silicone

treated on one side

Applications

Electrodes: ECG, EKG, TENS

AED defibrillator pads

Medical device mounting

Transdermal delivery system

Features Benefits

| • F | Polyethylene Foam Backing | Soft and flexible for maximum patient comfort | | | | |
|-----|---------------------------|---|-------------------------------|--|--|--|
| | • | Conformable and easily adapts to medical | | | | |
| | | levices and b | ody contours | | | |
| • A | • | Strong adhesi | on to surfaces | | | |
| | | Stable to EtO | and gamma sterilization | | | |
| • 8 | 96lb Kraft Liner | Easily die-cut | into various shapes and sizes | | | |
| | | Dimensionally | stable and moisture resistant | | | |

Typical Test Values

| | Standard | ndard UOM Metric UOM | | UOM | Test Method | | | | |
|-------------------------|----------|----------------------|-------|------|--------------|--|--|--|--|
| Total Thickness w/liner | 40.0 | mils | 1.016 | mm | PSTC 133 | | | | |
| Adhesive Thickness | 2.0 | mils | 0.051 | mm | PSTC 133 | | | | |
| Carrier Thickness | 31.2 | mils | 0.792 | mm | PSTC 133 | | | | |
| Liner Thickness | 6.8 | mils | 0.173 | mm | PSTC 133 | | | | |
| Adhesion to Steel | 90 | oz/in | 9.85 | N/cm | PSTC 101 Mod | | | | |
| Duaduat Cafatu | | | | | | | | | |

Product Safety

The base adhesives in this medical product have been tested in accordance with ISO 10993 and found to be non-cytotoxic, non-irritating, and non-sensitizing.

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F

The information presented herein was prepared at BERRY GLOBAL, INC. by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.

