



|                                                      |                        |             |
|------------------------------------------------------|------------------------|-------------|
| <b>TEST REPORT</b>                                   | <b>PRODUCT:</b>        | <b>156M</b> |
| FORD ESB-M3G76-B2 (2005-SEP-26)                      | <b>TEST SUBSTRATE:</b> | ABS         |
| DOCUMENT TITLE: TAPE, POLYESTER - PRESSURE SENSITIVE | <b>REPORT DATE:</b>    | 06/26/23    |

| <u>PARAGRAPH</u>                       | <u>REQUIREMENT</u> | <u>ABS Results</u> |
|----------------------------------------|--------------------|--------------------|
| 3.6 180° PEEL ADHESION [ASTM D 1000] ❶ |                    |                    |
| 3.6.1 Immediate                        | 219 N/m Minimum    | 590 N/m            |
| 3.6.2 72 hour dwell                    | 657 N/m Minimum    | 876 N/m            |
| 3.6.3 5 Thermal Cycles                 | 438 N/m Minimum    | 1238 N/m           |
| 3.7 MIGRATION STAIN ❷                  | None               | N/A                |
| 3.8 LINER REMOVAL                      | 55 N/m Maximum     | 5.95 N/m           |

❶ Adchem adhesive system backed exposed-side with 1 mil PET film

❷ Not Tested. Requires current production white enameled panel prepared per FLTM BI 103-02.

APPROVED:

Original Test Date: 9/14/21  
Berry Global Technical Service Department

*Conditioning and Testing per FORD ESB-M3G76-B2*