



TEST REPORT	PRODUCT:	3175M O	
GMW16443 Type 1 & 2 [Interior] – August, 2018	TEST SUBSTRATE:	20%TFPP & ABS	
DOCUMENT TITLE: Adhesion Performance Requirements for Adhesive Backed Light Trim and Foam	REPORT DATE:	06/26/23	
PARAGRAPH	REQUIREMENT	20% TFPP <u>RESULTS</u>	ABS <u>RESULTS</u>
<ul> <li>3 REQUIREMENTS</li> <li>3.3.3 EDGE ADHESIVE</li> <li>3.5.3 As Received</li> <li>3.5.4 Heat Aged – 168H @ 80 ± 2°C [ISO 188] ●</li> </ul>	No Signs of Lift or Separation from the Bonded to Substrate. During	No Signs of Lift or Separation From Bonded Substrate and No adhesive flow during Heat Exposure Observed	
<ul> <li>3.5.5 Humidity – 168H @ 38° ± 2°C &amp; 98% RH  ● </li> <li>3.5.6 Cycle Exposure – GMW14124 Cycle C  ● </li> </ul>	Heat Exposure, the Adhesive Must Not Flow		
<ul> <li>3.4 180° PEEL ADHESION [ISO 8510-2]</li> <li>3.5.3 As Received</li> <li>3.5.4 Heat Aged – 168H @ 80 ± 2°C [ISO 188] </li> <li>3.5.5 Humidity – 168H @ 38° ± 2°C &amp; 98% RH </li> <li>4 Cycle Exposure – GMW14124 Cycle C </li> </ul>	525 N/m Minimum and Foam Tear <b>€</b>	840 N/m 1068 N/m 935 N/m 985 N/m	1047 N/m 1432 N/m 1332 N/m 1292 N/m
3.5.8 <b>COLD SHOCK</b> [GMW16443] Impact [With No Recover] 180° Peel Adhesion [ISO 8510-2]	Must Withstand 525 N/m Minimum	Pass 1024 N/m	Pass 1188 N/m

**Note:** Accelerated Weathering Resistance per 3.5.7 for parts "if exterior exposed" not tested. Testing would require application part and substrate.

- Adchem adhesive system backed exposed-side with 1 mil PET film
- EXCEPTION: Samples conditioned in laboratory standard Gravity Convection oven not specifically designed to comply with ISO 188.
- EXCEPTION: Samples conditioned at 38°C and 98% Non-Condensing Humidity in place of Condensing Humidity per GMW14729 Option A (Water Fog)
- EXCEPTION: 38°C and 98% Non-Condensing Humidity used in place of Condensing Humidity per GMW14729
   2 Cycles: 17h -30 +/- 2 °C, 72h 70 +/- 2 °C, 24h 38°C and 98% RH, 7h -30 +/- 2 °C, 17h 38°C and 98% RH, 7h 70 +/- 2 °C, 24h 38°C and 98% RH
- EXCEPTION: Demonstration of Foam Tear as stated requires proposed foam/adhesive combination tested on the production intent substrate.
  - ♦ Results for this test are Non-Accredited Data due to Exception as stated

APPROVED: Original Test Date: 7/28/21 Berry Global Technical Service Department

Conditioning and Testing per GMW16443 Type 1 & 2 Except as Noted

1852 Old Country Rd Riverhead, NY 11901 631-727-6000 • www.berryglobal.com