



| TEST REPORT | PRODUCT: | 4373M |
|--|-----------------|----------|
| FORD ESB-M3G76-B2 (2005-SEP-26) | TEST SUBSTRATE: | ABS |
| DOCUMENT TITLE: TAPE, POLYESTER - PRESSURE SENSITIVE | REPORT DATE: | 06/26/23 |

| <u>PARAGRAPH</u> | | I | REQUIREMENT | ABS <u>Results</u> |
|------------------|-------|-------------------------------------|-----------------|-----------------------|
| 3.6 | | PEEL ADHESION M D 1000] ① | | |
| | 3.6.1 | Immediate | 219 N/m Minimum | 666 N/m |
| | 3.6.2 | 72 hour dwell | 657 N/m Minimum | 797 N/m |
| | 3.6.3 | 5 Thermal Cycles | 438 N/m Minimum | 706 N/m |
| 3.7 | MIGRA | ATION STAIN 2 | None | N/A |
| 3.8 | LINER | REMOVAL | 55 N/m Maximum | 53.6 N/m |

- Adchem adhesive system backed exposed-side with 1 mil PET film
- 2 Not Tested. Requires current production white enameled panel prepared per FLTM BI 103-02.
- 1 Liner removal tested as reverse-backing release (pulling 1 mil PET backed adhesive layer from liner).

APPROVED:

Original Test Date: 9/14/21

Berry Global Technical Service Department