

<b>TEST REPORT</b>	<b>PRODUCT:</b>	<b>4373M ①</b>
FORD WSS-M99P48-A3 JUL 2016 ➤ INTERIOR, AT OR ABOVE BELTLINE	<b>TEST SUBSTRATE:</b>	20% Talc-Filled Polypropylene [TFPP], ABS & TPO
DOCUMENT TITLE: FOAM PERFORMANCE, PRESSURE SENSITIVE ADHESIVE TAPE WSS-M99P48-A3 (INTERIOR, EXTERIOR, CLIMATE CONTROL AND UNDERHOOD)	<b>REPORT DATE:</b>	06/26/23

PARAGRAPH SUBSTRATE	REQ	RESULTS		
		<u>TFPP</u>	<u>ABS</u>	<u>TPO</u> ◆
3.2 DURABILITY REQUIREMENTS AND CHARACTERIZATION OF PRODUCTION MATERIALS				
3.2.8 Original  ASTM D1000, SECTION 46-53 EXCEPT REPLACE THE STEEL PANELS WITH THE INTENDED SUBSTRATE, 180 DEGREE PEEL	0.48 N/mm Minimum	0.19 N/mm ▲	0.67 N/mm	0.46 N/mm ▲
3.2.8.1 After Heat Aging Change  At or Above Beltline [168 hours, 100 +/- 2 °C]	-25% Max	-	0.72 N/mm	-
3.2.8.2 After Environmental Cycling Change  10 cycles, each cycle shall consist of the following:  • 4 h at 100 +/- 2 °C • 4 h at 38 +/- 2 °C and 95-100% R.H. • 16 h at -40 +/- 2 °C	-25% Max	-	0.60 N/mm	-

◆ Solvay Sequel 1402

① Adhesive tested with 1-mil PET film applied to exposed-side of adhesive

▲ Results in **RED** do not meet minimum peel adhesion requirement

APPROVED:

Original Test Date: 12/07/20  
 Berry Global Technical Service Department

Conditioning and Testing per FORD WSS-M99P48-A3

1852 Old Country Rd Riverhead, NY 11901  
 631-727-6000 • [www.berryglobal.com](http://www.berryglobal.com)