

TEST REPORT	PRODUCT: 654M
Ford WSS-M11P62-A; 2017 07 05	TEST SUBSTRATE: N/A
DOCUMENT TITLE: ADHESIVE, INTERIOR PERFORMANCE	REPORT DATE: 06/26/23

.5	REQUIREMENTS	Requirement	Results	Status
3.0	STANDARD REQUIREMENT FOR PRODUCTION MATERIALS			
3.4	FLAMMABILITY ✦ (ISO 3795)	100 mm/min Max	0 ✦ Self Extinguishing	PASS
3.5	ODOR ◆ (SAE J 1351)			
	DRY:	2 Max	2 Slight, but noticeable odor	PASS
	WET:	2 Max	2 Slight, but noticeable odor	PASS
3.6	FOGGING ✦ ✦ (SAE J1756, 3 h at 100 C heating, 21 C cooling plate, post test conditioning 1 h and 16 h)			
	1 HOUR:	70 Minimum	95 ✦ Dry Uniform	PASS
	16 HOUR:	70 Minimum	93 ✦ Dry Uniform	PASS

✦ Sample tested applied to aluminum foil.

✦ Results as reported from independent test laboratory.

◆ Results for this test are Non-Accredited Data

APPROVED: Original Test Date: 5/14/2018
Adchem Technical Service Department

Conditioning and Testing per WSS-M11P62-A except as noted