


## Differential Double-Coated Tape



**Liner:** 60# Polycoated Kraft

**Liner Side Adhesive:** Rubber (I915)

**Backing/Carrier:** 0.5 mil PET Film

**Air Side Adhesive:** Rubber (I917)

### Applications

- Bonding to a wide variety of PU and PE foams, felt, cork, rubber, and sponge materials
- Splicing applications
- Weatherstripping
- General purpose bonding uses
- Gasket, insulation, light shielding, and sound damping uses

### Features

- Differential Rubber Adhesive System
- Polyester Film Carrier
- 60# Polycoated Kraft Liner

### Benefits

- Air-side offers exceptional high tack
- Liner-side well-suited for general purpose use
- Support for aid in processing and application
- Conformable
- Excellent lay flat properties
- Clean die-cuts

### Typical Test Values

	Standard UOM	Metric UOM	Test Method
<b>Overall Thickness (w/liner)</b>	7.7 mils	0.196 mm	PSTC 133
<b>Air-Side Adhesive Thickness</b>	1.4 mils	0.036 mm	PSTC 133
<b>Carrier Thickness</b>	0.5 mils	0.013 mm	PSTC 133
<b>Liner Side Adhesive Thickness</b>	1.3 mils	0.033 mm	PSTC 133
<b>Liner Thickness</b>	4.5 mils	0.114 mm	PSTC 133
<b>Adhesion to Steel (Air Side)</b>	145 oz/in	15.86 N/cm	PSTC 101 Mod - 1 mil PET
<b>Adhesion to Steel (Liner Side)</b>	125 oz/in	13.68 N/cm	PSTC 101 Mod - 1 mil PET
<b>Adhesion to Steel (Air Side)</b>	230 oz/in	25.16 N/cm	PSTC 101 Mod - 2 mil Alu Foil
<b>Adhesion to Steel (Liner Side)</b>	220 oz/in	24.07 N/cm	PSTC 101 Mod - 2 mil Alu Foil
<b>Shear Strength</b>	>24 Hours		PSTC 107 Mod
<b>Laminating Temperature</b>	68 to 100 °F	20 to 38 °C	
<b>Service Temperature</b>	30 to 150 °F	-1 to 66 °C	

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

Standard Shelf Life: 12 months from date of shipment

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.