


6801 P

Rubber Transfer Tape



Release Liner

Liner:

2 mil Clear PET Film

Adhesive

Adhesive:

Rubber (I915)

Applications

- Laminating expanded polystyrene foam used in the packaging industry

Features

Benefits

- | | |
|---|--|
| <ul style="list-style-type: none"> • Rubber Adhesive • PET Film Liner | <ul style="list-style-type: none"> • High peel strength • Excellent initial tack • Good shear strength • Improved die-cutting and kiss cutting • Ideal for hot-wire cutting |
|---|--|

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Adhesive Thickness	1.2 mils	0.030 mm	PSTC 133
Liner Thickness	2.0 mils	0.051 mm	PSTC 133
Adhesion to Steel	70 oz/in	7.66 N/cm	PSTC 101 Mod - 1 mil PET
Shear Strength (at 72 °F)	>7 Days		PSTC 107 Mod
Laminating Temperature	68 to 100 °F	20 to 38 °C	
Service Temperature	30 to 150 °F	-1 to 66 °C	

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

Standard Shelf Life: 12 months from date of shipment

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.